

Coating recommendation

Measure:	Final coating with Aqua 2DS-450/10 at the construction site
Component:	IMI concrete floor covering
Cut:	Grind the surface with a grinding pad (green) and then remove the dust. The substrate must be load-bearing and dry as well as free of grease, wax, dirt and dust.
Product:	Aqua 2DS-450/10 + 10% Aqua H-480 + 4% texturing agent SM-820/M + 10% water.
Type of application:	Rolls with velour roller 3-4 mm
Application rate:	80-100 g/m ²
Drying:	min. 8 hours at 20°C

We would like to point out that this description of services/execution does not claim to be complete, as this requires a detailed examination of the object. Therefore no liability can be assumed. If new, previously unknown circumstances arise during the execution of the work, these must be taken into account.

The compatibility, adhesion and colour shade with the substrate must be checked by applying test surfaces. Please refer to the Technical Data Sheets, which you can also download from the Internet at www.remmers.com, for information on processing our products.